



# 182 Monocrystalline Bifacial PERC Solar Cell


efficiency of testing production

**23.3~23.7%**




Dimension : 182mm × 182mm ± 1.5mm

Cell Thickness : 182mm ± 18 μm




**JH18210BBA01**

## Front



## Back



## Electrical Performance

Grade	Unit	23.60	23.50	23.40	23.30	23.20	23.10	23.00	22.90	22.80
Voc	V	0.692	0.691	0.690	0.689	0.688	0.687	0.686	0.685	0.684
Isc	A	13.848	13.833	13.818	13.803	13.783	13.775	13.767	13.747	13.735
Vmpp	V	0.595	0.594	0.593	0.592	0.591	0.590	0.589	0.588	0.587
Imp	A	13.210	13.190	13.169	13.148	13.122	13.105	13.088	13.067	13.042
Pmpp	W	7.85	7.82	7.79	7.76	7.73	7.69	7.66	7.63	7.59

Standard Test Conditions: 1000W/m<sup>2</sup>, AM1.5, 25 °C

## Physical Characteristics

Substrate material	P-type mono-crystalline silicon wafer-PERC	Front (-)	10*0.08mm ±0.03mm bus bars (silver) 168 lines, Silicon oxide + blue silicon nitride compound anti reflection coating(PID Free)
Cell thickness	160μm ±16μm	Back (+)	1.2 ±0.3mm wide soldering pads (silver), Aluminum oxide and Aluminum lines back-surface field, Laser design of vertical bus bars
Dimension	182mm*182mm ±0.5mm		
Diagonal	247mm ±0.5mm		

## Temperature Coefficient

TkPower	-(0.39±0.02) %/k
TkVoltage	-(0.33±0.03) %/k
TkCurrent	+(0.06±0.015) %/k

## Anti-PID

Potential Induced Degradation(-1500V,192h):<5%

## Packaging, Storage

Solar cells are closely packed with soft sponge around and heat shrink is used around the box unit. Outer packing box must have shock buffer, to be suitable for long-distance delivery.

After packaging, cells should be stored indoors in the conditions of humidity below 60%, and temperature (20 ± 10) °C. Cells should be sampling inspected again if the storage time over 90 days.

## Light induced degradation test

Using Xenon lamp (Irradiance of 1000W/m<sup>2</sup>, with spectrum AM 1.5) to irradiate test cells, after a total irradiation of 5 kwh/m<sup>2</sup>, the degradation of maximum output power of cells is ≤2%